

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
22 August 2002 (22.08.2002)

PCT

(10) International Publication Number
WO 02/064250 A2

(51) International Patent Classification⁷: B01J 31/24

(21) International Application Number: PCT/EP02/01036

(22) International Filing Date: 31 January 2002 (31.01.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
01300866.9 31 January 2001 (31.01.2001) EP

(71) Applicant (for all designated States except US): SHELL
INTERNATIONALE RESEARCH MAATSCHAPPIJ
B.V. [NL/NL]; Carel van Bylandtlaan 30, NL-2596 HR
The Hague (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): ARNOLDY, Peter
[NL/NL]; Badhuisweg 3, NL-1031 CM Amsterdam (NL).
BOLINGER, Cornelius, Mark [US/US]; 514 Oyster
Creek Drive, Sugar Land, TX 77478 (US). DRENT,
Eit [NL/NL]; Badhuisweg 3, NL-1031 CM Amsterdam
(NL). EBERHARD, Michael, Rolf [DE/GB]; Cantocks
Close, Bristol, Avon BS8 1TS (GB). HEERES, Hero,
Jan [NL/NL]; Badhuisweg 3, NL-1031 CM Amster-
dam (NL). VAN DER LINDEN, Adrianus, Johannes
[NL/NL]; Volmerlanen 8, NL-2288 GD Rijswijk (NL).
MUL, Wilhelmus, Petrus [NL/NL]; Badhuisweg 3,

NL-1031 Cm Amsterdam (NL). PRINGLE, Paul, Gerard
[GB/GB]; Cantocks Close, Bristol, Avon BS8 1TS (GB).
SUYKERBUYK, Jacoba, Catherina, Lucia, Johanna
[NL/NL]; Badhuisweg 3, NL-1031 CM Amsterdam (NL).
TAU, Kwoliang, David [US/US]; 17103 Rolling Brook
Ct., Sugar Land, TX 77479 (US).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR,
GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR,
NE, SN, TD, TG).

Published:

— without international search report and to be republished
upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: PROCESS FOR THE CARBONYLATION OF ETHYLENICALLY UNSATURATED COMPOUNDS, BIDENTATE
DIPHOSPHINE COMPOSITION USED IN THIS PROCESS AND PROCESSES FOR PREPARATION OF THIS BIDENTATE
DIPHOSPHINE COMPOSITION

(57) Abstract: Process for the carbonylation of optionally substituted ethylenically unsaturated compounds by reaction with carbon
monoxide and a coreactant in the presence of a catalyst system. The catalyst system includes (a) a source of Pt group metal cations,
(b) a bidentate diphosphine composition. More than 60% w/w of bidentate diphosphine present in the bidentate diphosphine com-
position has the general formula (II) X¹-R-X² wherein X¹ and X² independently represent an optionally substituted symmetrical
phosphabicycloalkyl group, having at least 5 ring atoms; and R represents a bivalent organic bridging group, connecting both phos-
phorus atoms. Bidentate diphosphine composition wherein more than 60% w/w of bidentate diphosphine present has the general
formula (II) X¹-R-X² wherein X¹ and X² independently represent an optionally substituted symmetrical phosphabicycloalkyl
group, having at least 5 ring atoms; and R represents a bivalent organic bridging group, connecting both phosphorus atoms, with
the proviso that the bidentate diphosphine is not 1,3-PP'bis(9-phosphabicyclo[3.3.1]nonyl)propane. In addition methods to prepare
such a bidentate diphosphine composition are described.

WO 02/064250 A2



PROCESS FOR THE CARBONYLATION OF ETHYLENICALLY
UNSATURATED COMPOUNDS, BIDENTATE DIPHOSPHINE COMPOSITION
USED IN THIS PROCESS AND PROCESSES FOR PREPARATION OF
THIS BIDENTATE DIPHOSPHINE COMPOSITION

Background of the invention

The present invention relates to a process for the
carbonylation of optionally substituted ethylenically
unsaturated compounds by reaction with carbon monoxide
and a coreactant in the presence of a catalyst system
5 comprising a source of Pt group metal cations and a
bidentate diphosphine having the general formula I



wherein Q^1 and Q^2 represent a phosphabicycloalkyl group,
10 having at least 5 ring atoms; and Z represents a bivalent
organic bridging group connecting both phosphorus atoms.

The present invention in particular relates to such
a reaction in which the coreactant is hydrogen.


A commercially important carbonylation reaction,
15 using hydrogen as coreactant, is the hydroformylation of
olefins, which are reacted with carbon monoxide and
hydrogen to form aldehydes and/or alcohols having one
carbon atom more than the precursor olefin. Depending on
catalyst, reaction conditions and substrates, the
20 hydroformylation can proceed with varying selectivities
to the several possible isomeric aldehydes or alcohols in
varying yields, as side reactions occur to a smaller or
larger extent. Generally only one isomeric product is
preferred. For many applications the presence of branched
25 aldehydes or alcohols is undesirable. Moreover, in view
of biological degradability, it is considered
advantageous to obtain products having a high content of

- 2 -

the linear isomer. The selectivity towards one of several possible isomeric products is called regioselectivity. For hydroformylation a regioselectivity towards reaction at the primary carbon atom, resulting in a linear product, is desirable.

WO-A-95/05354 describes the carbonylation of ethylenically unsaturated compounds by reaction with carbon monoxide and hydrogen, i.e. hydroformylation, in the presence of a catalyst system comprising a Group VIII metal cation, viz. cationic palladium and platinum, and a bidentate ligand, viz. a diphosphine. In the examples amongst others 1,2-bis(1,4-cyclooctylene phosphino)ethane, i.e. in IUPAC nomenclature 1,2-PP'bis(9-phosphabicyclo[4.2.1]nonyl)ethane; 1,3-bis(1,4-cyclooctylene phosphino)propane, i.e. in IUPAC nomenclature 1,3-PP'bis(9-phosphabicyclo[4.2.1]nonyl)-propane; and 1,2-bis(2,6-dimethyl, 1,4-cyclooctylene phosphino)ethane, i.e. in IUPAC nomenclature 1,2-PP'bis(2,6-dimethyl, 9-phosphabicyclo[4.2.1]nonyl)-ethane are used as bidentate diphosphine ligands. The phosphabicyclononyl groups in these ligands are all substituted or non-substituted 1,4-cyclooctylenephosphino groups, i.e. in IUPAC nomenclature 9-phosphabicyclo[4.2.1]nonyl groups. Such a 9-phosphabicyclo[4.2.1]nonyl group is visualised in Figure A.

Figure A




As is illustrated by the examples the hydroformylation of ethylenically unsaturated compounds with a catalyst system containing these diphosphines results in acceptable selectivities towards the linear product.

- 3 -

The 9-phosphabicyclo[4.2.1]nonyl group visualized in Figure A is an example of an asymmetrical phosphabicycloalkyl group. In an asymmetrical phosphabicycloalkyl group the bridges not containing the phosphorus atom have an unequal number of atoms in the bridge. By a symmetrical phosphabicycloalkyl group is understood that the bridges (i.e. the hydrocarbyl groups connecting the tertiary carbon atoms), which do not contain the phosphorus atom, have an equal number of atoms. An example of such a symmetrical group is the 9-phosphabicyclo[3.3.1]nonyl group which is visualised in Figure B.

Figure B



WO-A-00/02375 describes a method to prepare a phosphorus-containing ligand by refluxing a phosphabicyclononane hydride with 1,2-dibromoethane in acetonitrile. After neutralisation with sodium hydroxide a bis-(9-phosphabicyclononyl)ethane can be isolated. The phosphabicyclononane hydride can conveniently be prepared as described by Elsner et al. (Chem. Abstr. 1978, vol. 89, 180154x).

In addition, non-pre-published WO-A-01/87899 describes the preparation of a bidentate diphosphine ligand by reacting P-cyclo-octyl hydride (e.g. phosphabicyclononane hydride) and butyllithium to generate a lithium cyclo-octyl phosphide and subsequently reacting with an appropriate substituted or non-substituted alkane diol sulphate ester. The P-cyclo-octyl hydride can conveniently be prepared as described by Elsner et al. (Chem. Abstr. 1978, vol. 89, 180154x).

- 4 -

In their article entitled "A simple procedure for the separation of the catalytically important phobane isomers" , published in Chemical Communications, 1997, pages 1527-1528, J.H. Downing et al. indicate that to
5 that date there had been no reports of the separation of the symmetrical and asymmetrical isomers of phosphabicyclononanes, although, by exploiting the difference in reactivity between the isomers, ligands derived from the symmetrical isomer had been isolated.

10 In the article of J.H. Downing et al. a laborious method is provided for separation of the isomers of phosphabicyclononane. The method comprises:

- a) reacting a mixture of both symmetrical and asymmetrical phosphabicyclononane hydride with
15 formaldehyde (CH_2O) in the presence of hydrochloric acid (HCl), yielding phosphonium salts;
- b) reacting these phosphonium salts with sodium hydroxide (NaOH), yielding a charged symmetrical phosphine and a neutral asymmetrical phosphine;
- 20 c) extracting the neutral asymmetrical phosphine with pentane, leaving relatively pure, charged symmetrical phosphine in an aqueous solution;
- d) treating the aqueous solution with sodium hydroxide to obtain the neutral symmetrical phosphine.

25 The symmetrical phosphabicyclononane is used in the synthesis of 1,3-PP'bis(9-phosphabicyclo[3.3.1]nonyl) propane. The overall yield of this preparation was only 17%. The article does not describe the preparation of any other bidentate diphosphine having general formula I.

30 Summary of the invention

Although good results with regard to the regio-selectivity towards a linear product are obtained in WO-A-95/05354, there is room for further improvement.


- 5 -

It is therefore an object of the present invention to provide a process for the carbonylation of ethylenically unsaturated compounds by reaction with carbon monoxide and a coreactant, which results in an improved regioselectivity towards a linear product.

It has now surprisingly been found that when a process for the carbonylation of ethylenically unsaturated compounds is characterised by a Pt group metal based catalyst comprising a specific bidentate diphosphine composition wherein a certain amount of bidentate diphosphine with two symmetrical phosphabicycloalkyl groups is present, unexpected advantages with regard to the regioselectivity towards a linear product are obtained.

Accordingly the present invention provides a process for the carbonylation of optionally substituted ethylenically unsaturated compounds by reaction with carbon monoxide and a coreactant in the presence of a catalyst system including:

- (a) a source of Pt group metal cations,
- (b) a bidentate diphosphine composition wherein more than 60% w/w of bidentate diphosphine present in the bidentate diphosphine composition has the general formula II



wherein X^1 and X^2 independently represent an optionally substituted symmetrical phosphabicycloalkyl group, having at least 5 ring atoms; and R represents a bivalent organic bridging group, connecting both phosphorus atoms.

The article of J.H. Downing et al. does not indicate any use, nor any expected advantage, for the 1,3-PP'bis(9-phosphabicyclo[3.3.1]nonyl) propane prepared. On the contrary, by means of reference 5,

- 6 -

referring to WO-A-95/05354, the article even indicates a preference for the asymmetrical phosphabicyclononyls.

As will be shown in the examples, however, the use of derivatives of symmetrical phosphabicycloalkane groups is very advantageous for the linearity of the product.

Detailed description of the invention

In the general formula II for component b) of the catalyst system, R preferably represents a bivalent organic bridging group containing from 1 to 10, preferably from 2 to 6, more preferably from 2 to 4, and most preferably 2 to 3 atoms in the shortest connection between both phosphorus atoms. Especially preferred is a bivalent organic bridging group having 2 atoms in this connection. Preferably, the bridging group R represents an alkylene group, but it can also comprise a carbon chain, interrupted by one or more hetero atoms, such as nitrogen, sulphur, silicon or oxygen atom. Preferably the shortest connection between both phosphorus atoms contains 2 or 3 carbon atoms, most preferably 2 carbon atoms.

The shortest connection between both phosphorus atoms can be substituted or non-substituted or can form part of a aliphatic or aromatic ring structure. In a preferred embodiment the connection forms part of an optionally substituted saturated or non-saturated aliphatic ring structure, such as for example a substituted or non-substituted cyclopentane, cyclopentene, cyclohexane or cyclohexene. The cycloaliphatic ring can be interrupted by one or more heteroatoms such as nitrogen, sulphur, silicon or oxygen atoms. The aliphatic ring structure can further be substituted with any kind of substituent, including heteroatoms, alkyl groups, cycloalkyl groups and aryl groups. If the connection forms part of an optionally substituted saturated or non-saturated aliphatic ring

- 7 -

structure the phosphorus atoms are preferably attached at adjacent positions, for example positions 1 and 2.

More preferably the connection is an ethylene or trimethylene group. Most preferably the connection is a
5 ethylene group. The connection can be a substituted alkylene group with at least one substituent and preferably at least two substituents. If the connection is substituted it is preferably substituted with two to four substituents, more preferably with two to three
10 substituents, and most preferably with two substituents.

The substituents can be attached to any part of the connection. In an advantageous embodiment, the carbon atoms of the connection, which are connected to the phosphorus atoms, are substituted. In this case the
15 bidentate diphosphine has two chiral C-atoms and can have the RR, SS, or R,S meso-form. The R,S meso-form is preferred.

The substituents can contain carbon atoms and/or hetero atoms. Substituents which can be used include
20 groups containing hetero-atoms such as halides, sulphur, phosphorus, oxygen and nitrogen. Examples of such groups include chloride, bromide, iodide, thiol, and groups of the general formula H-O-, A¹-O-, -S-A¹, -CO-A¹, -NH₂, -NHA¹, -NA¹A², -CO-NA¹A², -OH, -PO₄, -NO₂, -NOH, -CO,
25 -SO₂, -SOH, in which A¹ and A², independently, represent aliphatic groups, preferably having from 1 to 10 carbon atoms, more preferably having from 1 to 4 carbon atoms, like methyl, ethyl, propyl and isopropyl.

Preferably the substituents are hydrocarbyl groups.
30 The hydrocarbyl groups themselves can be aromatic, aliphatic or cycloaliphatic. The hydrocarbyl groups can contain carbon atoms and hetero atoms. Hydrocarbyl groups can further include groups containing hetero-atoms such as the ones mentioned hereinabove. The hydrocarbyl groups

- 8 -

can be straight-chain or branched, and can contain saturated and/or non-saturated links.

Aromatic hydrocarbyl substituent groups can be aryl groups such as phenyl groups and alkyl phenyl groups.

5 Preferred hydrocarbyl substituent groups are alkyl groups, preferably having from 1 to 10 carbon atoms, more preferably from 1 to 4 carbon atoms. Linear, branched or cyclic alkyl groups can be used. Alkyl groups can be methyl, ethyl, propyl, iso-propyl, butyl and iso-butyl.
10 More preferably methyl groups are used.

Most preferably the bivalent bridging group R is an ethylene group which is di-substituted, preferably with two alkyl groups, most preferably with two methyl groups.

X^1 and X^2 independently represent a substituted or
15 non-substituted symmetrical phosphabicycloalkyl group. Of the three bridges present in such a phosphabicycloalkyl group, the bridge containing the phosphorus atom is preferably the shortest one. As explained above, the other two bridges have an equal length, i.e. contain an
20 equal number of atoms in the bridge. By "a bridge" is meant a connection between both tertiary carbon atoms.

Preferred are symmetrical phosphabicycloalkyl groups with at least 7 ring atoms (of which one is, of course, a phosphorus atom) and preferably with from 7 to 11 ring
25 atoms. More preferably X^1 and X^2 represent a substituted or non-substituted symmetrical phosphabicyclononyl group. Examples of symmetrical phosphabicycloalkyl groups therefore include substituted or non-substituted
2-phosphabicyclo[1.1.1]pentyl; 2-phosphabicyclo[2.1.1]-
30 hexyl; 2-phosphabicyclo[3.1.1]heptyl; 3-phosphabicyclo[3.1.1]heptyl; 7-phosphabicyclo[2.2.1]heptyl; 2-phosphabicyclo[2.2.2]octyl; 2-phosphabicyclo[5.1.1]nonyl; 3-phosphabicyclo[5.1.1]nonyl; 4-phosphabicyclo[5.1.1]nonyl; 2-phosphabicyclo[3.2.2]nonyl; 3-phospha-

- 9 -

bicyclo[3.2.2]nonyl; 9-phosphabicyclo[3.3.1]nonyl;
9-phosphabicyclo[3.3.2]decyl; 2-phosphabicyclo-
[3.3.3]undecyl; 3-phosphabicyclo [3.3.3] undecyl. Of
these, substituted or non-substituted 7-phospha-
5 bicyclo[2.2.1]heptyl; 9-phosphabicyclo[3.3.1]nonyl;
9-phosphabicyclo[3.3.2] decyl are preferred. Particularly
preferred are substituted or non-substituted 9-phospha-
bicyclo[3.3.1]nonyl groups.

X^1 and X^2 can each represent a different symmetrical
10 phosphabicycloalkyl or can both represent the same
phosphabicycloalkyl. Preferably both X^1 and X^2 represent
the same symmetrical phosphabicycloalkyl, preferably a
symmetrical 9-phosphabicyclo[3.3.1]nonyl group.

One or both of the phosphabicycloalkyl rings can be
15 substituted with one or more hydrocarbyl groups
containing carbon atoms and/or hetero atoms. If a
phosphabicycloalkyl ring is substituted, preferably one
or both of the bridges not containing the phosphorus atom
is substituted, preferably with one or more alkyl groups,
20 preferably having from 1 to 10 carbon atoms, more
preferably from 1 to 4 carbon atoms. Linear, branched or
cyclic alkyl groups can be used. Preferred alkyl groups
include methyl, ethyl, propyl, iso-propyl, butyl and iso-
butyl. More preferably methyl groups are used. The
25 substituted phosphabicycloalkyl ring can be mono- or
poly-substituted and is preferably di-substituted. Most
preferably the phosphabicycloalkyl ring is substituted
with two methyl groups. Examples of substituted phosphabicycloalkyl rings include 3,7 dimethyl,9-phospha-
30 bicyclo[3.3.1]nonyl; 3,7 diethyl,9-phosphabicyclo[3.3.1]-
nonyl; 2,6-dimethyl, 9-phosphabicyclo[3.3.1]nonyl.

Preferred bidentate diphosphines of formula II
include 1,2-P,P'bis(9-phosphabicyclo[3.3.1]nonyl)ethane;
1,3-P,P'bis(9-phosphabicyclo[3.3.1]nonyl)propane;

- 10 -

1,2-P,P'bis(9-phosphabicyclo[3.3.1]nonyl)propane;
2,3-P,P'bis(9-phosphabicyclo[3.3.1]nonyl)butane;
2,3-P,P'bis(9-phosphabicyclo[3.3.1]nonyl)pentane;
2,4-P,P'bis(9-phosphabicyclo[3.3.1]nonyl)pentane;
5 1,2-P,P'bis(3,7-dimethyl, 9-phosphabicyclo[3.3.1]-
nonyl)ethane; 1,3-P,P'bis(3,7-dimethyl, 9-phos-
phabicyclo[3.3.1]nonyl)propane; 1,2-P,P'bis(3,7-dimethyl,
9-phosphabicyclo[3.3.1]nonyl)propane; 2,3-P,P'bis(3,7-
dimethyl, 9-phosphabicyclo[3.3.1]nonyl)butane;
10 2,3-P,P'bis(3,7-dimethyl, 9-phosphabicyclo[3.3.1]-
nonyl)pentane; 2,4-P,P'bis(3,7-dimethyl, 9-phos-
phabicyclo[3.3.1]nonyl)pentane; 1,2-P,P'bis(9-phos-
phabicyclo[3.3.1]nonyl)cyclopentane; 1,2-P,P'bis(9-phos-
phabicyclo[3.3.1]nonyl)cyclohexane; and mixtures thereof.

15 These bidentate diphosphines can be prepared with
methods as described in WO-A-00/02375 and/or non-pre-
published WO-A-01/87899.

Especially preferred are 1,2-P,P'bis(9-phos-
phabicyclo[3.3.1]nonyl)ethane; 1,2-P,P'bis(9-phos-
20 phabicyclo[3.3.1]nonyl)propane; and 2,3-P,P'bis(9-phos-
phabicyclo[3.3.1]nonyl)butane. Most preferred is
2,3-P,P'bis(9-phosphabicyclo[3.3.1]nonyl)butane.

Preferably more than 80% w/w and more preferably
more than 85% w/w of the bidentate diphosphine present in
25 the bidentate diphosphine composition of component (b) of
the catalyst system has the general formula (II). Even
more preferably in the range of from 90% w/w, more
preferably of from 95% w/w to 100% w/w of the bidentate
diphosphine present in the composition has the general
30 formula (II). Most preferably in the range of from 99%
w/w to 100% w/w of the bidentate diphosphine present in
the composition has the general formula (II).

Examples of sources of Pt group metal cations of
component (a) of the catalyst system are platinum or
35 palladium compounds such as salts of palladium and nitric

- 11 -

acid, sulphuric acid or sulphonic acids, salts of platinum or palladium and carboxylic acids with up to 12 carbon atoms, palladium or platinum complexes, e.g. with carbon monoxide or acetylacetonate, or palladium
5 combined with a solid material such as an ion exchanger. Palladium(II) acetate and platinum(II) acetylacetonate are examples of preferred metal sources.

Some of the catalyst systems which can be used in the process according to the present invention are novel.
10 Accordingly, the present invention provides a catalyst system including:

- (a) a source of Pt group metal cations,
 - (b) a bidentate diphosphine composition
- wherein more than 60% w/w of bidentate diphosphine
15 present in the bidentate diphosphine composition has the general formula (II)



wherein X^1 and X^2 independently represent an optionally substituted symmetrical phosphabicycloalkyl group, having
20 at least 5 ring atoms; and R represents a bivalent organic bridging group, connecting both phosphorus atoms. Preferences for components (a) and (b) are as described hereinbefore.

Preferably the catalyst system also includes as an
25 additional component (c) a source of anions. As anion source, any compound generating these anions can be used. Acids, or salts thereof, can be used as source of anions, for example any of the acids mentioned above, which can also participate in the salts of the metals of the
30 platinum group.

In the process of the present invention, preferably acids are used as anion source having a pKa value of less than 6, more preferably less than 5, measured in aqueous solution at 18 °C.

- 12 -

Typical examples of anions which can be used are anions of phosphoric acid, sulphuric acid, sulphonic acids and halogenated carboxylic acids such as trifluoroacetic acid.

5 Sulphonic acids are in particular preferred, for example methanesulphonic acid, trifluoromethanesulphonic acid, tert-butane-sulphonic acid, p-toluenesulphonic acid and 2,4,6-trimethylbenzene-sulphonic acid.

Also, complex anions can be used, such as the anions
10 generated by a combination of a Lewis acid such as BF_3 , AlCl_3 , SnF_2 , $\text{Sn}(\text{CF}_3\text{SO}_3)_2$, SnCl_2 or GeCl_2 , with a protic acid, such as a sulphonic acid, e.g. $\text{CF}_3\text{SO}_3\text{H}$ or $\text{CH}_3\text{SO}_3\text{H}$ or a hydrohalic acid such as HF or HCl , or a combination of a Lewis acid with an alcohol. Examples of such complex
15 anions are BF_4^- , SnCl_3^- , $[\text{SnCl}_2.\text{CF}_3\text{SO}_3]^-$ and PF_6^- .

The ethylenically unsaturated compound, used as starting material, is preferably an alkene having from 2 to 20 carbon atoms per molecule, or a mixture thereof. Preferred are alkenes having from 3 to 20 and more
20 preferably from 3 to 14 carbon atoms, or mixtures thereof. They can comprise one or more double bonds per molecule but alkenes having 1 to 3 carbon-carbon double bonds per molecule are preferred. The alkene can be substituted or non-substituted. Preferred substituents
25 include alkyl and aryl groups as well as groups containing hetero-atoms such as halides, sulphur, phosphorus, oxygen and nitrogen. Examples of substituents include chloride, bromide, iodide and hydroxy, alkoxy, carboxy, amino, amido, nitro, cyano, thiol or thioalkoxy
30 groups. Examples of ethylenically unsaturated compounds include ethene, propene, 1-butene, 2-butene, isobutene, pentenes, hexenes, octenes and dodecenes, 1,5-cyclo-octadiene, cyclododecene, methyl pentenoates and pentene nitriles.

- 13 -

In the process of the present invention, these ethylenically unsaturated compounds can be converted by reaction with carbon monoxide and a coreactant with a high regioselectivity towards the linear product.

5 In the process of the present invention, the ethylenically unsaturated starting material and the formed product can act as reaction diluent. Hence, the use of a separate solvent is not necessary. Conveniently, however, the carbonylation reaction can be carried out in
10 the additional presence of a solvent. As such, saturated hydrocarbons, e.g. paraffins and isoalkanes, are recommended and furthermore alcohols, the saturated hydrocarbons and alcohols preferably having from 4 to 10 carbon atoms per molecule, such as butanol,
15 ethylhexanol-1, nonanol-1, or in general terms the alcohols formed as carbonylation product; ethers such as 2,5,8-trioxanonane (diglyme), diethylether and anisole, and ketones, such as methylbutylketone. Solvents, comprising or substantially consisting of sulphones are
20 also preferred. Sulphones are in particular preferred, for example dialkylsulphones such as dimethylsulphone and diethylsulphone and cyclic sulphones, such as sulfolane (tetrahydrothiophene-2,2-dioxide), sulfolane, 2-methyl-sulfolane and 2-methyl-4-ethylsulfolane.

25 The quantity in which the catalyst system is used is not critical and can vary within wide limits. Usually amounts in the range of 10^{-8} to 10^{-1} , preferably in the range of 10^{-7} to 10^{-2} mole atom of platinum group metal per mole of ethylenically unsaturated compound are used.
30 The amounts of the participants in the catalyst system are conveniently selected such that per mole atom of platinum group metal from 0.5 to 10, preferably from 1 to 6 moles of bidentate diphosphine are used, from 0.5 to

- 14 -

15, preferably from 1 to 8 moles of anion source or a complex anion source.

Furthermore the presence of a small amount of catalyst promoter comprising a source of halide anions can have a significant favourable effect in that the conversion reaction proceeds at high rate, even at moderate temperatures, with very little formation of saturated hydrocarbons.

For hydroformylation the coreactant can be molecular hydrogen, or more generally a hydride source. The carbon monoxide and hydrogen can be supplied in equimolar or non-equimolar ratios, e.g. in a ratio within the range of 5:1 to 1:5, preferably 3:1 to 1:3. More preferably they are supplied in a ratio within the range of 2:1 to 1:2.

The carbonylation can be carried out at moderate reaction conditions. Hence temperatures in the range of 50 to 200 °C are recommended, preferred temperatures being in the range of 70 to 160 °C. Reaction pressures in the range of 500 to 10000 kPa (5 to 100 bar) are preferred; lower or higher pressures can be selected, but are not considered particularly advantageous. Moreover, higher pressures require special equipment provisions.


The claimed catalyst system can also be useful in conversion reactions other than hydroformylation. In general the coreactant can be represented by NuH, wherein Nu represents the remnant nucleophilic moiety of the coreactant after removal of a hydrogen atom. The nature of the coreactant largely determines the type of product formed. The coreactant can be a nucleophilic compound having a mobile hydrogen atom, such as an alcohol, an acid, an amine or water. For an alcohol XOH (X being the carbon containing part), the XO moiety is represented by Nu and accordingly the product is an ester.

- 15 -

Similarly, the use of an acid XCOOH ($\text{Nu} = \text{XCOO}$) will introduce an anhydride group in the product of the mono-carbonylation reaction; the use of ammonia ($\text{Nu} = \text{NH}_2$) or an amine XNH_2 ($\text{Nu} = \text{XNH}$) or X_2NH ($\text{Nu} = \text{X}_2\text{N}$) will
5 introduce an amide group; the use of a thiol XSH ($\text{Nu} = \text{XS}$) will introduce a thioester group; and the use of water ($\text{Nu} = \text{OH}$) will introduce a carboxy group.

Some of the bidentate diphosphine compositions which can be used in the process according to the present
10 invention are novel.

Accordingly the present invention also provides a bidentate diphosphine composition wherein more than 60% w/w of bidentate diphosphine present has the general formula II



wherein X^1 and X^2 independently represent an optionally substituted symmetrical phosphabicycloalkyl group, having at least 5 ring atoms; and R represents a bivalent organic bridging group, connecting both phosphorus atoms,
20 with the proviso that the bidentate diphosphine is not 1,3-PP'bis(9-phosphabicyclo[3.3.1]nonyl)propane.

Preferably more than 80% w/w and more preferably more than 85% w/w of the bidentate diphosphine present in the bidentate diphosphine composition has the general
25 formula (II). Even more preferably in the range of from 90% w/w, more preferably of from 95% w/w, to 100% w/w of the bidentate diphosphine present in the composition has the general formula (II). Most preferably in the range of from 99% w/w to 100% w/w of the bidentate diphosphine
30 present in the composition has the general formula (II). Preferences for the bidentate diphosphine itself are as described above for the process.

- 16 -

Bidentate diphosphine compositions wherein a bidentate diphosphine is present having the general formula II are known in the art. For example, US-A-3527818 describes in example I a mixture of
5 octamethylene-PP'-bis(9-phosphabicyclo[4.3.1]nonane), octamethylene-PP'-bis(9-phosphabicyclo[3.3.1]nonane) and octamethylene-P-(9-phosphabicyclo[4.2.1]nonane)P' (9-phosphabicyclo[3.3.1]nonane). To obtain a bidentate
10 diphosphine composition which can be used in the process of the present invention, however, such compositions/ mixtures need to be purified to obtain a higher percentage of bidentate diphosphine having the general formula (II).

The preparation of a purified bidentate diphosphine
15 composition, that is a bidentate diphosphine composition wherein the percentage of bidentate diphosphine having the general formula (II) is as specified above, can be established by one or more of the following 3 ways:
I. Purification of the starting compound. That is,
20 separation of the symmetrical phosphabicycloalkane from a composition of symmetrical and asymmetrical phosphabicycloalkanes to obtain a composition with a high percentage of symmetrical phosphabicycloalkane. Bidentate diphosphines are subsequently prepared from the
25 composition having a high percentage of symmetrical phosphabicycloalkanes.

II. The use of specific reaction conditions during the preparation of bidentate diphosphines from a composition of phosphabicycloalkanes, such that reaction towards a
30 bidentate diphosphine having general formula (II) is favoured.

III. Purification of a composition of bidentate diphosphines itself. That is, separation of the bidentate diphosphines with general formula (II) from a composition
35 of bidentate diphosphines to obtain a composition with a

- 17 -

high percentage of bidentate diphosphines with general formula (II).

Preferably the presence of oxygen during all processes is avoided as much as possible in order to avoid the formation of oxides of the phosphabicycloalkanes and/or bidentate diphosphines. Most preferably processes are conducted under essentially oxygen-free conditions. Thus, preferably compounds used, such as for example solvents and solutions, are deoxygenated before use. In addition, the process is preferably conducted in an oxygen-free environment, for example by applying an atmosphere of nitrogen during all manipulations.

I. Purification of a starting compound.

Preferably the starting compound is purified to the extent that the resulting phosphabicycloalkane composition comprises more than 60% w/w, preferably more than 80% w/w, more preferably at least 90% w/w and even more preferably in the range of 95 to 100% w/w of symmetrical phosphabicycloalkane. Most preferably the resulting composition is essentially 100% w/w pure, that is it comprises in the range of from 99% w/w, most preferably of from 99.5% w/w to 100% w/w of symmetrical phosphabicycloalkane.

An example of the purification of a composition comprising symmetrical and asymmetrical phosphabicycloalkanes is given by J.H. Downing et al. in their article entitled "A simple procedure for the separation of the catalytically important phobane isomers", published in Chemical Communications, 1997, pages 1527-1528, which is described hereinbefore. A disadvantage of this method, however, is that it involves a number of chemical reactions, such as a reaction with formaldehyde. The use of chemical reactions slows down the process.

A novel method for the purification of a composition comprising symmetrical and asymmetrical phosphabi-

- 18 -

cycloalkanes which does not involve such chemical reactions has now been found. Surprisingly it was found that symmetrical and asymmetrical phosphabicycloalkanes can be separated by exploiting a difference found in
5 basicity between the symmetrical and asymmetrical isomer of a phosphabicycloalkane.

The present invention therefore also provides a process for the separation of symmetrical phosphabicycloalkane from a composition containing
10 symmetrical and asymmetrical phosphabicycloalkanes comprising the following steps:

- a) adding means to protonate a phosphabicycloalkane to a composition containing symmetrical phosphabicycloalkane (SPBA) and asymmetrical phosphabicycloalkane (APBA),
15 yielding a composition comprising protonated symmetrical phosphabicycloalkane (SPBA+) and non-protonated asymmetrical phosphabicycloalkane (APBA);
- b) separating protonated symmetrical phosphabicycloalkane (SPBA+) and non-protonated asymmetrical phosphabicycloalkane (APBA), yielding separated protonated symmetrical phosphabicycloalkane (SPBA+) and separated non-protonated asymmetrical phosphabicycloalkane (APBA)
20
- c) adding means to de-protonate the separated protonated symmetrical phosphabicycloalkane (SPBA+),
25 yielding separated non-protonated symmetrical phosphabicycloalkane (SPBA).

The novel process is faster and more easy to conduct than the process described in the article of J. Downing et al. In addition the reversibility in protonating and
30 deprotonating the phosphabicycloalkanes make it a "forgiving" process.

By "protonate a phosphabicycloalkane" is meant that a phosphabicycloalkane accepts a proton, i.e. a positively charged hydrogen atom (H+).

- 19 -

Preferred means to protonate a phosphabicycloalkane include a wide range of acids, such as hydrohalic acids, e.g. hydrogen chloride, hydrogen bromide, hydrogen iodide and hydrogen fluoride; halogen oxo acids, e.g. hypobromous acid, chlorous acid, hypochlorous acid, perchloric acid and periodic acid; mineral acids, e.g. sulphuric acids, nitric acids and phosphoric acids; some organic acids, such as acetylacetic acids, sulphonc acids, carboxylic acids and halogenated carboxylic acids e.g. trichloroacetic acid and trifluoroacetic acid; complex acids such as HBF_4 , HSnCl_3 ; and mixtures of those acids.

More preferred are inorganic acids such as the hydrohalic acids, halogen oxo acids and mineral acids mentioned. More preferred are hydrohalic acids of which HCl , HI , and HBr are most preferred.

Preferred means to de-protonate the separated protonated symmetrical phosphabicycloalkane (SPBA^+) in step c) include a wide range of bases, such as ammonia and primary, secondary and tertiary amines; carbonates and hydrogencarbonates, such as for example Na_2CO_3 , NaHCO_3 , K_2CO_3 , MgCO_3 ; and hydroxides such as $\text{Ba}(\text{OH})_2$, $\text{Na}(\text{OH})$ and $\text{K}(\text{OH})$. More preferred are alkali metal hydroxides, such as potassium hydroxide and sodium hydroxide.

Preferably the separation in step b) is achieved by making use of a difference in solubility of SPBA^+ and APBA . Preferably a composition containing SPBA and APBA is solved in a solvent which does not dissolve SPBA^+ . Means to protonate a phosphabicycloalkane, such as for example a hydrohalogenic acid, can be added to the dissolved phosphabicycloalkanes as a gas, as a (dissolved) liquid or a solid, whichever is most suitable. For example a HCl gas or a 1 M aqueous solution

- 20 -

of HCl can be added to a diethylether solution of phosphabicycloalkanes. The SPBA⁺ can subsequently be separated as a precipitated solid or as a solution in a second liquid phase. The precipitate can, however, be thick and sticky and difficult to handle in isolation and purification.

Preferably the separation in step b) is therefore achieved by phase separation. An especially preferred process for the separation of symmetrical phosphabicycloalkane from a composition containing symmetrical and asymmetrical phosphabicycloalkanes accordingly comprises:

- i) dissolving a composition containing SPBA and APBA in a suitable non-water miscible solvent, which does not dissolve SPBA⁺, yielding a non-aqueous phosphabicycloalkane (PBA) solution;
- ii) combining the non-aqueous PBA solution with an aqueous solution of a suitable acid, yielding an aqueous phase containing protonated SPBA⁺ and a non-aqueous phase containing non-protonated APBA;
- iii) separating the aqueous phase containing protonated SPBA⁺ and the non-aqueous phase containing non-protonated APBA, yielding an aqueous solution containing protonated SPBA⁺ and a non-aqueous solution containing non-protonated APBA;
- iv) combining the aqueous solution containing protonated SPBA⁺ with a suitable non-water miscible solvent and an aqueous solution of a suitable base, yielding a non-aqueous solution containing non-protonated SPBA;
- v) removing the solvent from the non-aqueous solution containing non-protonated SPBA, yielding separated SPBA.

Optionally an extra step vi) is added to the process comprising removing the solvent from the non-aqueous solution containing non-protonated APBA, yielding separated APBA.

- 21 -

By a non-water miscible solvent is meant a hydrophobic solvent. Such a solvent can be mixed with water but upon standing two phases will eventually separate.

5 A wide range of non-water miscible solvents are available in which SPBA and APBA can be solved and which do not dissolve SPBA+. By not dissolving SPBA+ is understood that this compound is essentially not dissolved, that is the molar ratio SPBA+ dissolved in the
10 solvent to SPBA+ dissolved in an aqueous 6 M HCl solution lies in the range from 10:90 to 0:100 and more preferably in the range from 5:95 to 0:100.

 Preferably the solvent is an aprotic solvent. Solvents which can be used include saturated and
15 unsaturated hydrocarbons, e.g. paraffins and linear, branched and cyclic alkanes, alkenes and alkynes, such as hexane, hexene, pentene and pentane, aromatics such as toluene and benzene; ethers, such as for example dimethylether anisole (methyl phenyl ether), 2,5,8-
20 trioxanonane (diglyme), diethylether, tetrahydrofuran, diphenylether, diisopropylether and the dimethylether of di-ethyleneglycol; esters, such as for example methylacetate, dimethyladipate, butyrolactone, propionates and pentenoates; ketones, such as
25 methylbutylketone and diethylketone; and sulphones, for example dialkylsulphones such as dimethylsulphone and diethylsulphone and cyclic sulphones, such as sulfolane (tetrahydrothiophene-2,2-dioxide), 2-methylsulfolane and 2-methyl-4-ethylsulfolane.

30 Preferred are aprotic solvents having a dielectric constant that is below a value of 50, more preferably in the range of 1 to 8, at 298.15 °K and 100 kPa (1 bar). In the present context, the dielectric constant for a given solvent is used in its normal meaning of representing the

- 22 -

ratio of the capacity of a condenser with that substance as dielectric to the capacity of the same condenser with a vacuum for dielectric. Values for the dielectric constants of common organic liquids can be found in
5 general reference books, such as the Handbook of Chemistry and Physics, 76th edition, edited by David R. Lide et al, and published by CRC press in 1995, and are usually quoted for a temperature of about 20 or 25 °C, i.e. about 293.15 or 298.15 °K, and atmospheric
10 pressure, i.e. about 100 kPa (1 bar), or can readily be converted to that temperature and pressure using the conversion factors quoted. If no literature data for a particular compound is available, the dielectric constant can be readily measured using established physico-
15 chemical methods.

For example, the dielectric constant of anisole is 4.3 (at 294.2 °K), of diethyl ether is 4.3 (at 293.2 °K), of sulfolane is 43.4 (at 303.2 °K), of diphenylether is 3.7 (at 283.2 °K), of dimethyladipate is 6.8 (at
20 293.2 °K), of tetrahydrofuran is 7.5 (at 295.2 °K), of methylnonanoate is 3.9 (at 293.2 °K), of toluene is 2.4 (at 296.4 °K), of pentane is 1.8 (at 293.2 °K).

Most preferred solvents are saturated alkanes and aromatics, such as hexane, pentane or toluene and ethers.
25 Ethers are especially preferred because the use of ethers in this separation process results in a quick and efficient phase-separation. Examples of ethers which can be used include dimethylether, methylethylether, anisole, diethylether and diphenylether.

30 Another especially preferred solvent is toluene, since toluene is less volatile and less flammable than some of the other solvents and therefore easy to handle.

- 23 -

In addition a phosphabicycloalkane composition is conveniently supplied as a toluene solution.

5 The concentrations of the reactants can be varied over a wide range, but is preferably kept high so as to reduce the amounts of solvent to be used. Phosphabicyclo-alkanes are preferably dissolved in the non-water miscible solvent to give a concentration in the range of 0.01 to 10 molar, more preferably in the range from 0.1 to 5 molar.

10 Preferred acids in step ii] are as described above for means to protonate a phosphabicycloalkane. Preferably concentrations in the range from 2 to 20 molar are used, and more preferably concentrations in the range from 5 to 15 molar are used. Most preferred are concentrations in
15 the range from 5 to 10 molar.

The aqueous solution of suitable acid in step ii] can be added as such to the non-aqueous PBA solution or can be prepared *in situ* by first adding water and subsequently adding acid in a more concentrated form.

20 Preferably a ratio of aqueous solution to non-aqueous solution in step ii] is used in the range from 1:10 to 10:1 v/v, more preferably in the range from 1:2 to 2:1 v/v.

25 After combining the non-aqueous PBA solution with a aqueous solution of suitable acid the system is preferably shaken or stirred, such to establish close contact between the acid and the phosphabicycloalkanes, whereafter the two phases are allowed to separate. The two phases are separated in step iii]. Preferably the
30 aqueous solution containing protonated SPBA⁺ is extracted one or more, preferably in the range from 1 to 50, times with a non-water miscible solvent as described for step i] to remove residues of non-protonated phosphabicycloalkanes and protonated APBA⁺.

- 24 -

Similarly the non-aqueous solution containing non-protonated APBA is preferably extracted one or more, preferably in the range from 1 to 50, times with a aqueous solution of a suitable acid to remove residues of protonated SPBA+.

Subsequently the aqueous solution containing protonated SPBA+ is combined in step iv] with a non-water miscible solvent as described for step i] and an aqueous solution of a suitable base, yielding a non-aqueous solution containing non-protonated SPBA;

Preferred bases are as described above for means to de-protonate the protonated symmetrical phosphabicyclo-alkane. Preferably concentrations in the range from 2 to 20 molar are used, and more preferably concentrations in the range from 5 to 15 molar are used.

Optionally residues of water are removed from the non-aqueous solutions yielded in steps iii] and/or iv] in a way known to one skilled in the art. For example residues of water can be removed by washing with bases such as hydroxides and carbonates, such as Na_2CO_3 , NaHCO_3 , K_2CO_3 , MgCO_3 , $\text{Ba}(\text{OH})_2$, $\text{Na}(\text{OH})$ and $\text{K}(\text{OH})$. Subsequently a non-aqueous solution can be dried over a drying agent such as for example K_2SO_4 , Na_2SO_4 and MgSO_4 .

Removal of the non-aqueous solvents in steps v] and vi] can be established in any way known to one skilled in the art to remove such solvents.


Further purification can be established by sublimation of the isomers. Preferably pressures in the range from 0.0033 to 0.33 kPa (0.025 to 2.5 mm Hg), more preferably in the range from 0.027 to 0.27 kPa (0.2 to 2 mm Hg) are used. Depending on the pressure applied, the temperatures can vary widely. Preferably a temperature in the range of 40 °C and higher is used, more preferably a temperature in the range from 40 °C to 90 °C is used.

- 25 -

II. The use of specific reaction conditions during the preparation of bidentate diphosphines

A preferred method for the preparation of some bidentate diphosphine ligands comprises refluxing a phosphabicycloalkane hydride, viz. 9-phosphabicyclononane hydride, with a α,ω -dihaloalkane, such as 1,2-dibromoethane or 1,3-diiodopropane in a suitable solvent. After neutralisation with a suitable basic compound the bidentate diphosphine can be isolated.

It has now been surprisingly found that by the use of specific reaction conditions a similar preparation process can be used to prepare a bidentate diphosphine composition wherein more than 60% w/w of bidentate diphosphine present has the general formula II



wherein X^1 and X^2 independently represent an optionally substituted symmetrical phosphabicycloalkyl group, having at least 5 ring atoms; and R represents a bivalent organic bridging group, connecting both phosphorus atoms.

The present invention therefore also relates to a process for the preparation of bidentate diphosphines having general formula (II) comprising:

- A1) heating a composition of phosphabicycloalkane hydrides with a α,ω -dihaloalkane in a suitable solvent, in a molar ratio of phosphabicycloalkane to α,ω -dihaloalkane of more than 2, yielding a charged bidentate diphosphine dihydride;
- A2) neutralisation of the charged bidentate diphosphine dihydride with a suitable basic compound, yielding a bidentate diphosphine composition wherein more than 60% w/w of bidentate diphosphine present has the general formula II.

- 26 -

Preferably the α,ω -dihaloalkane is a α,ω -dibromo-alkane, α,ω -dichloroalkane or α,ω -diiodoalkane.

The molar ratio of phosphabicycloalkane to α,ω -dihaloalkane is preferably more than 3, more preferably more than 4 and most preferably in the range more than 4 to 20.

The solvent used in step A1) can be any solvent found suitable for the process. Preferred solvents include saturated hydrocarbons, e.g. paraffins and linear, branched and cyclic alkanes, such as hexane and pentane, aromatics such as toluene and benzene; nitriles such as for example acetonitrile and alkanols such as for example ethanol, methanol and isopropanol and mixtures of two or more of those. Especially preferred solvents are acetonitrile, hexane, ethanol and toluene, and mixtures of two or more of those.

Preferably the basic compound in step A2) is ammonia or a primary, secondary and tertiary amine or a hydroxide such as $\text{Ba}(\text{OH})_2$, $\text{Na}(\text{OH})$ or $\text{K}(\text{OH})$. More preferred are alkali metal hydroxides, such as potassium hydroxide and sodium hydroxide.

It is further found that the preparation of bidentate diphosphine having the general formula II is enhanced by the use of an alkanol as a solvent.

The present invention therefore also relates to a process for the preparation of bidentate diphosphines having general formula (II)



wherein X^1 and X^2 independently represent an optionally substituted symmetrical phosphabicycloalkyl group, having at least 5 ring atoms; and R represents a bivalent organic bridging group, connecting both phosphorus atoms, comprising:

- 27 -

B1) heating a composition of phosphabicycloalkane hydrides with a α,ω -dihaloalkane in an alkanol, yielding a charged bidentate diphosphine dihydride;

B2) neutralisation of the charged bidentate diphosphine dihydride with a suitable basic compound, yielding a bidentate diphosphine composition wherein more than 60% w/w of bidentate diphosphine present has the general formula II.

Preferred alkanols in step B1) are methanol, ethanol and isopropanol. Most preferred is ethanol. Preferences for α,ω -dihaloalkane, the molar ratio of phosphabicycloalkane to α,ω -dihaloalkane, and the basic compound in step B2) are as described hereinabove for the steps A1) and A2).

15 III. Purification of a composition of bidentate diphosphines.

A further method for the preparation of a bidentate diphosphine composition wherein more than 60% w/w of the bidentate diphosphine present has the general formula (II), comprises purification of a bidentate diphosphine composition wherein 60% w/w or less of the bidentate diphosphine present has the general formula (II).

Now a very advantageous method has been found for purification of such a composition wherein 60% w/w or less of the bidentate diphosphine present has the general formula (II). Surprisingly it was found that a bidentate diphosphine with two symmetrical phosphabicycloalkyl groups (s,s BDP), i.e. a bidentate diphosphine with general formula (II), can be separated from a composition comprising a mixture of bidentate diphosphine with two symmetrical phosphabicycloalkyl groups (s,s BDP), bidentate diphosphine with two asymmetrical phosphabicycloalkyl groups (a,a BDP) and bidentate diphosphine

- 28 -

with a symmetrical and an asymmetrical phosphabicycloalkyl group (a,s BDP), by exploiting a difference found in solubility.

The present invention therefore also provides a
5 process for separation of a bidentate diphosphine with two symmetrical phosphabicycloalkyl groups (s,s BDP) from a mixture of bidentate diphosphines with two symmetrical phosphabicycloalkyl groups (s,s BDP), bidentate
10 diphosphines with two asymmetrical phosphabicycloalkyl groups (a,a BDP) and bidentate diphosphines with a symmetrical and a symmetrical phosphabicycloalkyl group (a,s BDP), comprising selective extraction and/or recrystallisation of the mixture in a suitable solvent.

Such a selective extraction and/or recrystallisation
15 was not known before. By selective is meant that isomers of a bidentate diphosphine with two phosphabicycloalkyl groups are extracted and/or recrystallised to a different extent. Preferably the selective extraction and/or
20 recrystallisation is carried out such that it yields a liquor containing a,a BDP and a,s BDP and a solid or suspension containing s,s BDP.

An advantage of the selective extraction and/or recrystallisation process is that the process is easy to perform. In addition, the process does not involve the
25 handling of toxic, volatile phosphabicycloalkanes for purification but the more easily handled bidentate diphosphine itself. Furthermore the process enables the preparation of bidentate diphosphine compositions with very high percentages of bidentate diphosphine having
30 general formula (II) by repeated recrystallisation steps.

Preferably a bidentate diphosphine composition is prepared wherein more than 80% w/w, more preferably more than 90% w/w, and even more preferably in the range of from 95 to 100% w/w of bidentate diphosphine present is
35 s,s BDP. More preferably a bidentate diphosphine

- 29 -

composition is prepared wherein in the range of from 99% w/w, most preferably of from 99.5% w/w to 100% w/w of bidentate diphosphine present is s,s BDP.

Preferred solvents for recrystallisation include
5 organic solvents such as saturated and unsaturated hydrocarbons, e.g. paraffins and linear, branched and cyclic alkanes and alkenes, such as hexane and pentane, cyclohexane, hexene, aromatics such as toluene and benzene; alkanols such as methanol, phenol, ethanol,
10 propanol, isopropanol, butanol, iso-butanol; ethers, such as for example dimethylether anisole (methyl phenyl ether), 2,5,8-trioxanonane (diglyme), diethylether, tetrahydrofuran, diphenylether, diisopropylether and the dimethylether of di-ethyleneglycol; esters, such as for
15 example methylacetate, dimethyladipate, butyrolactone, propionates and pentenoates; ketones, such as acetone, methylethylketone, methylbutylketone and diethylketone; and sulphones, for example dialkylsulphones such as dimethylsulphone and diethylsulphone and cyclic
20 sulphones, such as sulfolane (tetrahydrothiophene-2,2-dioxide), 2-methylsulfolane and 2-methyl-4-ethylsulfolane and mixtures of one or more of those or mixtures thereof with water.

Preferred solvents are alkanols and ketones,
25 preferably those comprising from 1 to 15 carbon atoms, and mixtures thereof with water. The use of alkanols or ketones or mixtures of those, optionally mixed with water, results in a high degree of separation and an attractive yield of s,s BDP.

30 More preferred solvents are alkanols, preferably those comprising from 1 to 10 carbon atoms and mixtures thereof with water. Most preferred are methanol, ethanol and isopropanol and mixtures thereof with water. Alkanols and mixtures of alkanols with water have the additional
35 advantage that any bidentate diphosphine oxides present

- 30 -

dissolve readily and can be easily separated from the s,s BDP, which dissolves to a much lesser extent. This opens opportunities to use an aged, partly oxidised starting bidentate diphosphine composition.

5 The amount of solvent used depends on whether a selective extraction or recrystallisation or a combination of those is carried out. Extraction can be economically more attractive because less solvent can be used and/or less energy is required for heating.

10 By extraction preferably a,a BPA and a,s BPA are extracted from the bidentate diphosphine compositions by repeated washings with a suitable solvent.

15 The temperature of the solvent depends on the solvent used, the amount of solvent used, and on the extent to which one wishes to dissolve (parts of) the bidentate diphosphine composition. Low temperatures and low amounts of solvent are economically more attractive.

20 Selective extraction and/or recrystallisation can be carried out by refluxing the composition of bidentate diphosphine in the solvent. The reflux temperature depends on the solvent used. Preferably solvents are used resulting in a reflux temperature in range of 5 to 200 °C, more preferably in the range of 15 to 150 °C.

25 Preferably the pressure during refluxing is in the range from 100 to 500 kPa (1 to 5 bar). Higher pressures have the advantage that a larger part of the bidentate diphosphine can be dissolved. Atmospheric pressures are economically more advantageous.

30 Preferably, the bidentate diphosphine is refluxed in a suitable solvent for 0.01 to 10 hours, more preferably in the range from 0.01 to 5 hours.

Extraction can be performed intermittently or continuously. In an intermittent extraction the bidentate diphosphine composition is preferably extracted in the

- 31 -

range from 1 to 20 times, as much as is sufficient to obtain the desired extraction of unwanted isomers. If possible, a small number of extractions, i.e. in the range from 1 to 5 times, is preferred for economical reasons. Preferably continuous extraction can be performed with a Soxhlet configuration.

The present invention will be illustrated by the following non-limiting examples.

Example 1

The experiment was carried out in a 250 ml magnetically stirred Hastelloy C autoclave (Hastelloy is a trademark). The autoclave was charged with 10 ml of propene, 40 ml anisole and 10 ml sulfolane, 0.25 mmol of platinum(II) acetylacetonate, 0.3 mmol of 1,2-PP'bis(9-phosphabicyclo[3.3.1]nonyl)ethane with a purity of > 99%, 0.3 mmol SnCl₂ and 0.3 mmol HCl. After being flushed, the autoclave was pressurised with carbon monoxide and hydrogen to a partial pressure of 3000 kPa (30 bar) of each. Subsequently, the reactor was sealed and the contents were heated to 115 °C and maintained at that temperature for 1.5 hours. After cooling, a sample was taken from the contents of the reactor and analysed by Gas Liquid Chromatography. The selectivity towards the linear product n-butyraldehyde was 98.6%.

Example 2

The experiment was carried out in a 250 ml magnetically stirred Hastelloy C autoclave. The autoclave was charged with 10 ml of propene, 40 ml anisole and 10 ml sulfolane, 0.25 mmol of platinum(II) acetylacetonate, 0.3 mmol of 1,3-PP'bis(9-phosphabicyclo[3.3.1]nonyl)-propane with a purity of > 99%, 0.3 mmol SnCl₂ and 0.3 mmol HCl. After being flushed, the autoclave was pressurised with carbon monoxide and hydrogen to a partial pressure of 3000 kPa (30 bar) of each.

- 32 -

Subsequently, the reactor was sealed and the contents were heated to 115 °C and maintained at that temperature for 1.5 hours. After cooling, a sample was taken from the contents of the reactor and analysed by Gas Liquid Chromatography. The selectivity towards the linear product n-butyraldehyde was 90.8%.

Example 3

The example was carried out in a 250 ml magnetically stirred Hastelloy C autoclave. The autoclave was charged with 10 ml of propene, 40 ml anisole and 10 ml sulfolane, 0.25 mmol of platinum(II) acetylacetonate, 0.3 mmol of meso (R,S) 2,3-PP'bis(9-phosphabicyclo[3.3.1]nonyl)butane with a purity of > 99% by weight, 0.3 mmol SnCl₂ and 0.3 mmol HCl. After being flushed, the autoclave was pressurised with carbon monoxide and hydrogen to a partial pressure of 3000 kPa (30 bar) of each. Subsequently, the reactor was sealed and the contents were heated to 100 °C and maintained at that temperature until the reaction was substantially complete. Complete propene conversion occurred in 0.5 hr. After cooling, a sample was taken from the contents of the reactor and analysed by Gas Liquid Chromatography. The selectivity towards the linear product n-butyraldehyde was 99.0%.

Example 4 (separation of phosphabicyclononanes)

A mixture of symmetrical and asymmetrical phosphabicyclononanes (33.9 g, 239 mmol, 153 mmol symmetrical: 86 mmol asymmetrical isomer) was dissolved in diethyl ether (240 ml). Subsequently deoxygenated water (240 ml) was added. The biphasic mixture was stirred vigorously while deoxygenated concentrated HCl solution (240 ml, 6 molar) was added over 90 min. The two phases were then separated and the aqueous phase was extracted 20 times with diethyl ether (50 ml each). The organic phases were combined (to reduce the volume, some

- 33 -

of the solvent can be removed in vacuum before continuing the work-up) and washed with a concentrated HCl solution (2 ml), and subsequently washed with a saturated NaHCO₃ solution (30 ml). Hereafter the organic solution was
5 dried over MgSO₄ and filtered over basic alumina. The solvent was removed in vacuum to give the asymmetrical isomer in a yield of 9.52 g (equivalent to 67.1 mmol, about 78% of amount of asymmetrical isomer started with) in a 100% purity as a colourless solid. To the vigorously
10 stirred aqueous phase fresh diethyl ether (200 ml) was added, the mixture was cooled to 0 °C and a 14.4 M NaOH solution (200 ml) was added over 1.5 h. The phases were separated and the aqueous phase was washed four times with diethyl ether (50 ml each). The combined organic
15 phases were dried over MgSO₄ and filtered over basic alumina. The solvent was removed in vacuum to give the symmetrical isomer in a yield of 19.79 g (equivalent to 139 mmol, about 91% of amount of asymmetrical isomer started with) in a 90% purity. Sublimation of the 90%
20 pure symmetrical isomer at 0.27 kPa (2 mm Hg) and 60 °C gave a sample of 98% pure symmetrical isomer in 80% recovery (15.83 g, 111 mmol) as a colourless solid.

All reactions in Examples 5-13 were carried out in an inert atmosphere (nitrogen). Solely p.a. grade
25 solvents were used which were obtained from Merck. 1,2-PP'bis (phosphabicyclononyl)ethane(BPE) compositions as specified for each example were analysed by ³¹P-NMR to indicate the amount of:

BPE-S = 1,2-PP'bis (phosphabicyclo[3.3.1]nonyl)ethane.
30 BPE-A = mixture of 1,2-PP'-bis(9-phosphabicyclo-[4.2.1]nonane) ethane, and 1-P-(9-phosphabicyclo-[4.2.1]nonane) 2-P' (9-phosphabicyclo[3.3.1]nonane) ethane.

- 34 -

BPE-O = mixture of oxides of 1,2-PP'bis(phosphabicyclopentyl)ethane

Example 5: isopropanol as solvent

A suspension of 2.67 gram of BPE (containing
5 2.05 gram of BPE-S) in 25 ml of isopropanol was refluxed
for 2 hrs. The now homogeneous solution was cooled to
ambient temperature (about 20 °C) and stirred for
16 hours. A white precipitate was formed which was
isolated by filtration under an atmosphere of nitrogen
10 and the purified product was dried at 0.1 kPa (1 mbar)
and 50 °C. Yield of BPE was 1.80 gram, containing 1.71
gram of BPE-S (84%). The liquid layer was evaporated to
dryness. Composition of precipitate and liquid layer was
analysed by ³¹P-NMR spectroscopy:

type BPE	precipitate	liquid layer
BPE-S	95.2	11.0
BPE-A	4.8	41.3
BPE-O	0.0	47.6

15 Example 6: methanol as solvent

2.33 gram of BPE (containing 1.74 gram of BPE-S) was
suspended in 25 ml of methanol. The suspension was
refluxed for 2 hours and subsequently stirred at ambient
temperature (about 20 °C) for 16 hours. The white
20 precipitate was isolated by filtration using Schlenk
techniques and dried in vacuum. Yield of BPE was
1.92 gram, containing 1.64 gram of BPE-S (94%). The
liquid layer was evaporated to dryness. The composition
of precipitate and liquid layer were analysed by ³¹P-NMR
25 spectroscopy:

- 35 -

type BPE	Precipitate	liquid layer
BPE-S	85.4	11.8
BPE-A	14.6	57.0
BPE-O	0.0	31.1

Example 7: extractions with methanol

A suspension of 3.4 gram of BPE (containing 2.65 gram of BPE-S) in 25 ml of methanol was stirred for 4 hours at ambient temperature (about 20 °C). The white precipitate was isolated by filtration using Schlenk techniques and dried in vacuum (1st extraction). Yield of BPE was 2.88 gram, containing 2.52 gram of BPE-S (95%). The liquid layer was evaporated to dryness. This procedure was repeated twice (2nd and 3rd extraction). All fractions were weighted and analysed by ³¹P-NMR spectroscopy.

	BPE starting material	preci- pitrate 1 st extraction	preci- pitrate 2 nd extraction	preci- pitrate 3 rd extraction
yield (gram) overall	3.4	2.8	2.3	1.8
BPE-S recovery (%)	-	92	85	70
BPE-S (%)	74.8	83.8	93.6	95.4
BPE-A (%)	21.8	11.8	6.4	4.6
BPE-O (%)	3.3	4.4	0.0	0.0

Example 8: Soxhlet extraction with methanol.

6.44 gram of BPE (containing 4.82 gram of BPE-S) was placed in a extraction filter and extracted with methanol for 2 hours in a Soxhlet configuration. The BPE material

- 36 -

was transferred to a round bottom flask and dried in vacuum. Yield of BPE was 4.4 gram, containing 3.92 gram of BPE-S (81%). The composition of precipitate and liquid layer were analysed by ^{31}P -NMR spectroscopy:

type BPE	precipitate	liquid layer
BPE-S	89.0	32.7
BPE-A	6.4	21.4
BPE-O	4.6	45.8

5 Example 9: Repetitive extraction with methanol/water
 (95/5 v/v)

 A suspension of 3.18 gram of BPE (containing 2.64 gram of BPE-S) in 100 ml of methanol/water (95/5 v/v, degassed with N_2) was refluxed for 2 hours.

10 After standing for 4 hours at ambient temperature (about 20 °C), the supernatant was decanted. The white precipitate was dried in vacuum (55 °C/0.1 kPa (1 mbar)). Yield of BPE was 2.50 gram, containing 2.37 gram of BPE-S (89%) (1st extraction). This procedure was repeated twice
15 (2nd and 3rd extraction). All fractions were weighted and analysed by ^{31}P -NMR spectroscopy. The percentage BPE-O in the precipitate was < 0.5% and was therefore omitted for the calculations.

- 37 -

	BPE starting material	preci- pitrate 1 st extraction	preci- pitrate 2 nd extraction	preci- pitrate 3 rd extraction
yield (gram) overall BPE-S	3.18	2.5	2.2	1.78
recovery (%)	-	89	81	73
BPE-S (%)	83.6	94.9	96.9	97.7
BPE-A (%)	16.3	5.1	3.1	2.3

Example 10: Extraction of BPE material using 100 ml portions methanol/water (90/10 v/v):

A suspension of 4.98 gram of BPE starting material (containing 3.47 gram of BPE-S) in 100 ml of methanol/-
5 water (90/10 v/v, degassed with N₂) was refluxed for 4 hours. After standing for 4 hours at ambient temperature (about 20 °C), the supernatant was decanted. The white precipitate was dried in vacuum (55 °C/0.1 kPa (1 mbar)). Yield of BPE was 3.72 gram, containing 3.34
10 gram of BPE-S (96%) (1st extraction). This procedure was repeated (2nd extraction). All fractions were weighted and analysed by ³¹P-NMR spectroscopy.

- 38 -

	BPE starting material	precipitate 1 st extraction	precipitate 2 ^{de} extraction
yield (gram)	4.98	3.34	3.47
overall BPE-S recovery (%)	-	96	94
BPE-S (%)	69.7	89.9	92.0
BPE-A (%)	16.5	8.4	5.6
BPE-O (%)	13.8	1.8	2.4

Example 11: Extraction of BPE material using 200 ml portions methanol/water (90/10 v/v):

A suspension of 5.00 gram of BPE material (containing 3.48 gram of BPE-S) in 200 ml of methanol/water (90/10 v/v, degassed with N₂) was refluxed for 19 hours. After standing for 1 hour at ambient temperature (about 20 °C), the supernatant was decanted. The white precipitate and supernatant were dried in vacuum (55 °C/0.1 kPa (1 mbar)). Yield of BPE was 2.98 gram, containing 2.74 gram of BPE-S (79%). Both fractions were weighted and analysed by ³¹P-NMR spectroscopy.

	BPE starting material	precipitate	liquid layer
yield (gram)	5.00	2.98	1.50
BPE-S recovery (%)	-	79	-
BPE-S (%)	69.7	92.1	9.3
BPE-A (%)	16.5	5.6	51.7
BPE-O (%)	13.8	2.3	39.0

- 39 -

Example 12: Extraction of BPE material with isopropanol/water (98/2 v/v)

A suspension of 5.30 gram of BPE material
 5 (containing 3.69 gram of BPE-S) in 40 ml of isopropanol
 and 0.8 ml of H₂O was refluxed for 6 hrs. The now
 homogeneous solution was cooled to ambient temperature
 (about 20 °C) and stirred for 16 hours. A white
 precipitate was formed which was isolated by filtration
 10 under an atmosphere of nitrogen and the purified product
 was dried (0.1 kPa (1 mbar)/60 °C). Yield of BPE was 3.50
 gram, containing 3.30 gram of BPE-S (89%). The liquid
 layer was evaporated to dryness. Composition of
 precipitate and liquid layer was analysed by ³¹P-NMR
 15 spectroscopy:

	BPE starting material	precipitate	filtrate
yield (gram)	5.30	3.50	1.60
BPE-S recovery (%)	-	89	-
BPE-S (%)	69.7	94.4	13.3
BPE-A (%)	16.5	3.4	44.4
BPE-O (%)	13.8	2.3	42.3

Example 13: Repetitive extraction of BPE material with methanol/water (95/5 v/v)

A suspension of 3.18 gram of BPE material
 (containing 2.64 gram of BPE-S) in 100 ml of
 20 methanol/water (95/5 v/v, degassed with N₂) was refluxed
 for 2 hours. After standing for 4 hours at ambient

- 40 -

temperature (about 20 °C), the supernatant was decanted. The white precipitate was dried in vacuum (55 °C/0.1 kPa(1 mbar)). Yield of BPE was 2.50 gram, containing 2.37 gram of BPE-S (89%) (1st extraction).

- 5 This procedure was repeated twice (2nd and 3rd extraction). All fractions were weighted and analysed by ³¹P-NMR spectroscopy. The percentage BPE oxides in the precipitate was < 0.5% and were therefore omitted for the calculations.


	BPE starting material	preci- pitrate 1 st extraction	preci- pitrate 2 nd extraction	preci- pitrate 3 rd extraction
yield (gram)	3.18	2.5	2.2	1.78
overall SS recovery (%)	-	89	81	73
BPE-S (%)	83.6	94.9	96.9	97.7
BPE-A (%)	16.3	5.1	3.1	2.3

- 41 -

C L A I M S

1. A process for the carbonylation of optionally substituted ethylenically unsaturated compounds by reaction with carbon monoxide and a coreactant in the presence of a catalyst system including:

- 5 (a) a source of Pt group metal cations,
(b) a bidentate diphosphine composition
wherein more than 60% w/w of bidentate diphosphine present in the bidentate diphosphine composition has the general formula II



wherein X^1 and X^2 independently represent an optionally substituted symmetrical phosphabicycloalkyl group, having at least 5 ring atoms; and R represents a bivalent organic bridging group, connecting both phosphorus atoms.

15 2. Catalyst system including:

- (a) a source of Pt group metal cations,
(b) a bidentate diphosphine composition
wherein more than 60% w/w of bidentate diphosphine present in the bidentate diphosphine composition has the
20 general formula (II)




wherein X^1 and X^2 independently represent an optionally substituted symmetrical phosphabicycloalkyl group, having at least 5 ring atoms; and R represents a bivalent
25 organic bridging group, connecting both phosphorus atoms.

3. Catalyst system as claimed in claim 2, wherein as an additional component (c) a source of anions is included.

- 42 -

4. Bidentate diphosphine composition wherein more than 60% w/w of bidentate diphosphine present has the general formula II



(II)

5 wherein X^1 and X^2 independently represent an optionally substituted symmetrical phosphabicycloalkyl group, having at least 5 ring atoms; and R represents a bivalent organic bridging group, connecting both phosphorus atoms, with the proviso that the bidentate diphosphine is not
10 1,3-PP'bis(9-phosphabicyclo[3.3.1]nonyl)propane.

5. A process for the separation of symmetrical phosphabicycloalkane from a composition containing symmetrical and asymmetrical phosphabicycloalkanes comprising the following steps:

15 a) adding means to protonate a phosphabicycloalkane to a composition containing symmetrical phosphabicycloalkane (SPBA) and asymmetrical phosphabicycloalkane (APBA), yielding a composition comprising protonated symmetrical phosphabicycloalkane (SPBA+) and non-protonated
20 asymmetrical phosphabicycloalkane (APBA);

b) separating protonated symmetrical phosphabicycloalkane (SPBA+) and non-protonated asymmetrical phosphabicycloalkane (APBA), yielding separated protonated symmetrical phosphabicycloalkane (SPBA+) and separated
25 non-protonated asymmetrical phosphabicycloalkane (APBA)

c) adding means to de-protonate the separated protonated symmetrical phosphabicycloalkane (SPBA+), yielding separated non-protonated symmetrical phosphabicycloalkane (SPBA).

30 6. A process for the separation of symmetrical phosphabicycloalkane from a composition containing symmetrical and asymmetrical phosphabicycloalkanes comprising:

- 43 -

- i] dissolving a composition containing symmetrical phosphabicycloalkane (SPBA) and asymmetrical phosphabicycloalkane (APBA) in a suitable non-water miscible solvent, which does not dissolve protonated symmetrical phosphabicycloalkane (SPBA+), yielding a non-
5 aqueous phosphabicycloalkane (PBA) solution;
ii] combining the non-aqueous PBA solution with an aqueous solution of a suitable acid, yielding an aqueous phase containing protonated SPBA+ and a non-aqueous phase
10 containing non-protonated APBA;
iii] separating the aqueous phase containing protonated SPBA+ and the non-aqueous phase containing non-protonated APBA, yielding an aqueous solution containing protonated SPBA+ and a non-aqueous solution containing non-
15 protonated APBA;
iv] combining the aqueous solution containing protonated SPBA+ with a suitable non-water miscible solvent and an aqueous solution of a suitable base, yielding a non-
aqueous solution containing non-protonated SPBA;
20 v] removing the solvent from the non-aqueous solution containing non-protonated SPBA, yielding separated SPBA.
7. Process as claimed in claim 6, wherein an extra step vi] is added to the process comprising removing the solvent from the non-aqueous solution containing non-
25 protonated APBA, yielding separated APBA.
8. Process for the preparation of bidentate diphosphines having general formula (II)



wherein X^1 and X^2 independently represent an optionally
30 substituted symmetrical phosphabicycloalkyl group, having at least 5 ring atoms; and R represents a bivalent organic bridging group, connecting both phosphorus atoms, comprising

- 44 -

A1) heating a composition of phosphabicycloalkane hydrides with a α,ω -dihaloalkane in a suitable solvent, in a molar ratio of phosphabicycloalkane to α,ω -dihaloalkane of more than 2, yielding a charged bidentate diphosphine dihydride;

A2) neutralisation of the charged bidentate diphosphine dihydride with a suitable basic compound, yielding a bidentate diphosphine composition wherein more than 60% w/w of bidentate diphosphine present has the general formula II.

9. Process for the preparation of bidentate diphosphines having general formula (II)



wherein X^1 and X^2 independently represent an optionally substituted symmetrical phosphabicycloalkyl group, having at least 5 ring atoms; and R represents a bivalent organic bridging group, connecting both phosphorus atoms, comprising

B1) heating a composition of phosphabicycloalkane hydrides with a α,ω -dihaloalkane in an alkanol, yielding a charged bidentate diphosphine dihydride;

B2) neutralisation of the charged bidentate diphosphine dihydride with a suitable basic compound, yielding a bidentate diphosphine composition wherein more than 60% w/w of bidentate diphosphine present has the general formula II.

10. Process for separation of a bidentate diphosphine with two symmetrical phosphabicycloalkyl groups (s,s BDP) from a mixture of bidentate diphosphines with two symmetrical phosphabicycloalkyl groups (s,s BDP), bidentate diphosphines with two asymmetrical phosphabicycloalkyl groups (a,a BDP) and bidentate diphosphines with a symmetrical and a symmetrical

- 45 -

phosphabicycloalkyl group (a,s BDP), comprising selective extraction and/or recrystallisation of the mixture in a suitable solvent.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
22 August 2002 (22.08.2002)

PCT

(10) International Publication Number
WO 02/064250 A3

(51) International Patent Classification⁷: **B01J 31/24**,
31/28, C07F 9/6568, C07C 45/50, 29/16, C07F 9/50

(21) International Application Number: PCT/EP02/01036

(22) International Filing Date: 31 January 2002 (31.01.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
01300866.9 31 January 2001 (31.01.2001) EP

(71) Applicant (*for all designated States except US*): SHELL
INTERNATIONALE RESEARCH MAATSCHAPPIJ
B.V. [NL/NL]; Carel van Bylandtlaan 30, NL-2596 HR
The Hague (NL).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): ARNOLDY, Peter
[NL/NL]; Badhuisweg 3, NL-1031 CM Amsterdam (NL).
BOLINGER, Cornelius, Mark [US/US]; 514 Oyster
Creek Drive, Sugar Land, TX 77478 (US). DRENT,
Eit [NL/NL]; Badhuisweg 3, NL-1031 CM Amsterdam
(NL). EBERHARD, Michael, Rolf [DE/GB]; Cantocks
Close, Bristol, Avon BS8 1TS (GB). HEERES, Hero,
Jan [NL/NL]; Badhuisweg 3, NL-1031 CM Amster-
dam (NL). VAN DER LINDEN, Adrianus, Johannes
[NL/NL]; Volmerlanan 8, NL-2288 GD Rijswijk (NL).
MUL, Wilhelmus, Petrus [NL/NL]; Badhuisweg 3,
NL-1031 CM Amsterdam (NL). PRINGLE, Paul, Gerard

[GB/GB]; Cantocks Close, Bristol, Avon BS8 1TS (GB).
SUYKERBUYK, Jacoba, Catherina, Lucia, Johanna
[NL/NL]; Badhuisweg 3, NL-1031 CM Amsterdam (NL).
TAU, Kwoliang, David [US/US]; 17103 Rolling Brook
Ct., Sugar Land, TX 77479 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR,
GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR,
NE, SN, TD, TG).

Published:

— with international search report

(88) Date of publication of the international search report:
30 January 2003

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 02/064250 A3

(54) Title: PROCESS FOR THE CARBONYLATION OF ETHYLENICALLY UNSATURATED COMPOUNDS, BIDENTATE DIPHOSPHINE COMPOSITION USED IN THIS PROCESS AND PROCESSES FOR PREPARATION OF THIS BIDENTATE DIPHOSPHINE COMPOSITION

(57) Abstract: Process for the carbonylation of optionally substituted ethylenically unsaturated compounds by reaction with carbon monoxide and a coreactant in the presence of a catalyst system. The catalyst system includes (a) a source of Pt group metal cations, (b) a bidentate diphosphine composition. More than 60% w/w of bidentate diphosphine present in the bidentate diphosphine composition has the general formula (II) X^1-R-X^2 wherein X^1 and X^2 independently represent an optionally substituted symmetrical phosphabicycloalkyl group, having at least 5 ring atoms; and R represents a bivalent organic bridging group, connecting both phosphorus atoms. Bidentate diphosphine composition wherein more than 60% w/w of bidentate diphosphine present has the general formula (II) X^1-R-X^2 , wherein X^1 and X^2 independently represent an optionally substituted symmetrical phosphabicycloalkyl group, having at least 5 ring atoms; and R represents a bivalent organic bridging group, connecting both phosphorus atoms, with the proviso that the bidentate diphosphine is not 1,3-PP'bis(9-phosphabicyclo[3.3.1]nonyl)propane. In addition methods to prepare such a bidentate diphosphine composition are described.

INTERNATIONAL SEARCH REPORT

national Application No
PCT/EP 02/01036

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B01J31/24 B01J31/28 C07F9/6568 C07C45/50 C07C29/16
C07F9/50

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B01J C07F C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, COMPENDEX, INSPEC

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 95 05354 A (SHELL INT RESEARCH ;SHELL CANADA LTD (CA)) 23 February 1995 (1995-02-23) cited in the application page 5, line 2 -page 6, line 15 claims 1,4-8, examples 53,54, table VI	1-4
Y		1
P,X	WO 01 87899 A (EBERHARD MICHAEL ROLF ;PRINGLE PAUL GERARD (GB); DRENT EIT (NL); S) 22 November 2001 (2001-11-22) cited in the application page 10, line 1-10 page 10, line 31 -page 11, line 14 page 12, line 15-27 page 16, line 5-25 claims 7-9	1-4
A	page 11, line 15 -page 12, line 6 -/-	8,9

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

23 September 2002

Date of mailing of the international search report

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Goebel, M

INTERNATIONAL SEARCH REPORT

national Application No

PCT/EP 02/01036

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB 2 306 344 A (SHELL INT RESEARCH) 7 May 1997 (1997-05-07) claims 1,6; example 1	1-4
Y	----	1
X	US 5 811 590 A (ARNOLDY PETER ET AL) 22 September 1998 (1998-09-22) claims 1,8; example 1	1-4
Y	claim 7	1
X	EP 0 529 698 A (SHELL INT RESEARCH) 3 March 1993 (1993-03-03) claims 1,8-10; example 7	1-4
Y	----	1
X	EP 0 495 547 A (SHELL INT RESEARCH) 22 July 1992 (1992-07-22) page 9, line 15 -page 10, line 2; claims 1,35	1-4
Y	----	1
X	WO 97 03943 A (SHELL INT RESEARCH ;SHELL CANADA LTD (CA)) 6 February 1997 (1997-02-06) page 5, line 20 - line 26 page 6, line 8 - line 24; claim 6	1-4
Y	----	1
X	EP 0 872 482 A (UNION CARBIDE CHEM PLASTIC) 21 October 1998 (1998-10-21) examples 34,36,37	1-4
A	WO 00 52017 A (ROBERTSON ALLAN JAMES ;CYTEC TECH CORP (US)) 8 September 2000 (2000-09-08) page 1, line 3 -page 2, line 5	1-4
X	US 6 037 500 A (ZHANG XUMU) 14 March 2000 (2000-03-14) see schemes 3, 4 column 17, line 13 -column 22, line 50; figures 5,11; examples 12,13; tables 7-9 column 8, line 55 - line 63	2-4
Y	----	1
A	----	8,9
X	EP 0 864 576 A (HOFFMANN LA ROCHE) 16 September 1998 (1998-09-16) page 2, line 1 - line 29; claims 1,7-10	2-4
A	----	8,9
X	US 6 080 898 A (JAGER WILLEM WABE ET AL) 27 June 2000 (2000-06-27) column 4, line 5 - line 8; examples 1-4; table I	2-4
	----- -/--	

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 02/01036

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 3 527 818 A (WINKLE JOHN L VAN ET AL) 8 September 1970 (1970-09-08) column 5, line 13-35; claim 3	4
A	---	1-3,5-10
X	US 5 304 686 A (SLAUGH LYNN H ET AL) 19 April 1994 (1994-04-19) column 3, line 17-34 claim 1	4
A	---	1-3,5-10
A	US 3 647 915 A (BAUER RONALD S ET AL) 7 March 1972 (1972-03-07) examples VII,VIII	5-7
X	CA 2 086 285 A (CANADA CYANAMID) 25 June 1994 (1994-06-25) examples claims 2,4,5,7-9,11-14	8
A	---	9
X	DOWNING J H ET AL: "A simple procedure for the separation of the catalytically important phosphabicyclononane isomers" CHEMICAL COMMUNICATIONS, ROYAL SOCIETY OF CHEMISTRY, GB, vol. 16, 21 August 1997 (1997-08-21), pages 1527-1528, XP002137315 ISSN: 1359-7345 cited in the application the whole document	4,8
A	---	5-7,9
X	GB 2 074 166 A (UNION CARBIDE CORP) 28 October 1981 (1981-10-28) claims; examples	10
X	WO 98 34941 A (ALBEMARLE CORP) 13 August 1998 (1998-08-13) claims; examples	10

INTERNATIONAL SEARCH REPORT

International application No.
PCT/EP 02/01036

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of Item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

see additional sheet

1. ☒ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

☐ The additional search fees were accompanied by the applicant's protest.

☒ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. Claims: 1-3

A process for the carbonylation of olefins and a catalyst system (i) suitable therefor, (i) comprising ligand (ii) and a source of Pt-group metal cations.

2. Claim : 4

A bidentate diphosphine composition wherein more than 60% (w/w) of diphosphine present therein has the general formula II, comprising two symmetrical phosphabicycloalkyl groups, e.g. a suitable ligand (ii) for the catalyst system (i).

3. Claims: 5-7

A process for the separation of any (sic) symmetrical phosphabicycloalkane (SPBA) from mixtures comprising its asymmetrical isomer (APBA), e.g. purification of an intermediate (iii) suitable for the synthesis of ligand (ii).

4. Claims: 8, 9

A process for the preparation of bidentate diphosphines composition wherein more than 60% (w/w) of diphosphine present has the general formula II, e.g. preparation of suitable ligands (ii) for the catalyst system (i) employing intermediates (iii).

5. Claim : 10

A process for the separation of any (sic) bidentate diphosphine (iv) with two symmetrical phosphabicycloalkyl groups (s,s BDP) from a mixtures of bidentate diphosphines comprising said s,s BDP, as well as its mono- and bis-asymmetrical isomers (a,s BDP and a,a BDP, respectively).

INTERNATIONAL SEARCH REPORT

Information on patent family members

national Application No

PCT/EP 02/01036

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9505354	A	23-02-1995	AU 7614194 A	14-03-1995
			BR 9407280 A	01-10-1996
			CN 1129438 A ,B	21-08-1996
			DE 69414578 D1	17-12-1998
			DE 69414578 T2	20-05-1999
			WO 9505354 A1	23-02-1995
			EP 0714385 A1	05-06-1996
			ES 2123823 T3	16-01-1999
			JP 9501917 T	25-02-1997
			SG 55063 A1	21-12-1998
			US 5488174 A	30-01-1996
WO 0187899	A	22-11-2001	AU 7404601 A	26-11-2001
			WO 0187899 A1	22-11-2001
			US 2002016484 A1	07-02-2002
GB 2306344	A	07-05-1997	ZA 9608894 A	23-10-1997
US 5811590	A	22-09-1998	AU 7298696 A	15-05-1997
			BR 9611126 A	30-03-1999
			CA 2234606 A1	01-05-1997
			CN 1200718 A	02-12-1998
			DE 69606427 D1	02-03-2000
			DE 69606427 T2	06-07-2000
			WO 9715543 A1	01-05-1997
			EP 0862546 A1	09-09-1998
			ES 2141540 T3	16-03-2000
			JP 11513702 T	24-11-1999
			ZA 9608895 A	09-12-1997
EP 0529698	A	03-03-1993	CA 2077007 A1	01-03-1993
			CN 1069960 A ,B	17-03-1993
			DE 69214572 D1	21-11-1996
			DE 69214572 T2	20-03-1997
			EP 0529698 A2	03-03-1993
			ES 2092627 T3	01-12-1996
			JP 5246916 A	24-09-1993
			KR 251076 B1	15-04-2000
			US 5214220 A	25-05-1993
EP 0495547	A	22-07-1992	CA 2059233 A1	16-07-1992
			CA 2059236 A1	16-07-1992
			CN 1063277 A ,B	05-08-1992
			DE 69204691 D1	19-10-1995
			DE 69204691 T2	11-04-1996
			DE 69210054 D1	30-05-1996
			DE 69210054 T2	12-12-1996
			EP 0495547 A2	22-07-1992
			EP 0495548 A2	22-07-1992
			ES 2088082 T3	01-08-1996
			ES 2077337 T3	16-11-1995
			JP 3233670 B2	26-11-2001
			JP 5058949 A	09-03-1993
			JP 3270098 B2	02-04-2002
			JP 4334340 A	20-11-1992
			KR 220824 B1	15-09-1999
			SG 45352 A1	16-01-1998
			US 5210280 A	11-05-1993

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 02/01036

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9703943	A	06-02-1997	AT 191448 T	15-04-2000
			AU 698153 B2	22-10-1998
			AU 6657796 A	18-02-1997
			BR 9609536 A	23-02-1999
			CA 2227063 A1	06-02-1997
			CN 1190951 A ,B	19-08-1998
			DE 69607621 D1	11-05-2000
			DE 69607621 T2	31-08-2000
			DK 839124 T3	28-08-2000
			WO 9703943 A1	06-02-1997
			EP 0839124 A1	06-05-1998
			ES 2144759 T3	16-06-2000
			HU 9802771 A2	29-03-1999
			JP 11509536 T	24-08-1999
			NO 980214 A	16-01-1998
			PL 324508 A1	25-05-1998
EP 0872482	A	21-10-1998	US 6184391 B1	06-02-2001
			EP 0872482 A2	21-10-1998
			US 6307065 B1	23-10-2001
			US 2001053858 A1	20-12-2001
WO 0052017	A	08-09-2000	AU 2982000 A	21-09-2000
			WO 0052017 A1	08-09-2000
US 6037500	A	14-03-2000	US 6207868 B1	27-03-2001
			US 6278024 B1	21-08-2001
			US 6399787 B1	04-06-2002
			US 2001047113 A1	29-11-2001
			AU 3397197 A	07-01-1998
			BR 9709790 A	10-08-1999
			CA 2258018 A1	18-12-1997
			CZ 9803937 A3	17-11-1999
			EP 0918781 A1	02-06-1999
			JP 2002513376 T	08-05-2002
			KR 2000016597 A	25-03-2000
			PL 330414 A1	10-05-1999
			TR 9802588 T2	21-12-2000
			WO 9747633 A1	18-12-1997
EP 0864576	A	16-09-1998	BR 9800862 A	21-03-2000
			CA 2230770 A1	10-09-1998
			CN 1193020 A	16-09-1998
			EP 0864576 A1	16-09-1998
			JP 10251281 A	22-09-1998
			US 6348612 B1	19-02-2002
US 6080898	A	27-06-2000	AU 736737 B2	02-08-2001
			AU 8863998 A	16-02-1999
			BR 9811017 A	26-09-2000
			CN 1264356 T	23-08-2000
			WO 9905085 A1	04-02-1999
			EP 1000003 A1	17-05-2000
			JP 2001510816 T	07-08-2001
			NO 20000300 A	21-01-2000
			TR 200000173 T2	21-09-2000
US 3527818	A	08-09-1970	US 3401204 A	10-09-1968

INTERNATIONAL SEARCH REPORT

Information on patent family members

national Application No

PCT/EP 02/01036

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3527818	A	GB 1127965 A BE 690123 A DE 1593466 A1 FR 1502250 A JP 49038278 B NL 6616540 A ,B	25-09-1968 24-05-1967 23-07-1970 18-11-1967 16-10-1974 29-05-1967
US 5304686	A 19-04-1994	AU 6039394 A BR 9405823 A CN 1117289 A ,B DE 69410442 D1 DE 69410442 T2 WO 9418149 A1 EP 0682650 A1 ES 2115936 T3 JP 8507048 T	29-08-1994 05-12-1995 21-02-1996 25-06-1998 15-10-1998 18-08-1994 22-11-1995 01-07-1998 30-07-1996
US 3647915	A 07-03-1972	BE 758343 A2 CA 987331 A1 DE 2053758 A1 FR 2068941 A5 GB 1303304 A JP 50023002 B NL 7015984 A ,B,	03-05-1971 13-04-1976 13-05-1971 03-09-1971 17-01-1973 05-08-1975 06-05-1971
CA 2086285	A 25-06-1994	CA 2086285 A1	25-06-1994
GB 2074166	A 28-10-1981	DE 3115292 A1 JP 1562735 C JP 56161398 A JP 62032759 B US 4710587 A	11-02-1982 12-06-1990 11-12-1981 16-07-1987 01-12-1987
WO 9834941	A 13-08-1998	EP 0970094 A1 US 5994587 A WO 9834941 A1	12-01-2000 30-11-1999 13-08-1998

